

REMARKS

Claims 1-12, as amended, remain herein. Claims 6 and 7 have been amended hereby and new claim 12 added.

This Preliminary Amendment is submitted to eliminate multiply dependent claims from the above-identified application.

Examination of this application on its merits is respectfully requested.

Respectfully submitted,

PARKHURST & WENDEL, L.L.P.



Roger W. Parkhurst
Registration No. 25,177

July 17, 2001
Date

Attachment:

Mark Up of Amended Claims

RWP/ame

Attorney Docket No. DAIN:580

PARKHURST & WENDEL, L.L.P.
1421 Prince Street, Suite 210
Alexandria, Virginia 22314-2805
Telephone: (703) 739-0220

09804084.074704

CLAIMS

1. An antireflection film comprising: a transparent layer formed of a cured product of an ionizing radiation-curable resin composition; and a concave-convex portion provided on one side of the transparent layer, the concave-convex portion comprising fine concaves and convexes provided at a pitch of not more than the wavelength of light.

2. The antireflection film according to claim 1, wherein the transparent layer is backed by a transparent substrate film.

3. The antireflection film according to claim 1, wherein the transparent layer has a surface hardness of not less than H in terms of pencil hardness.

4. The antireflection film according to claim 1, which further comprises, provided on the concaves and convexes, a layer formed of a resin composition having lower light refractive index than the transparent layer.

5. The antireflection film according to claim 1, which has antistatic properties.

6. A polarizing element comprising: a polarizing plate; and, stacked on the polarizing plate, the antireflection film according to ~~any one of claims 1 to 5~~ claim 1.

7. A display device comprising: a display section; and, stacked or disposed on the display section in its viewer side, the antireflection film according to ~~any one of claims 1 to 5~~ or the polarizing element according to claim 6 claim 1.

8. A process for producing an antireflection film, comprising the steps of: providing a mold with an uneven surface having fine concaves and convexes at a pitch of not more than the wavelength of light; applying, onto the mold, an ionizing radiation-curable resin composition in an amount large enough to at least fill the concaves of the mold surface; after the application of the ionizing radiation-curable resin composition, covering the top of the applied resin composition with a transparent substrate film; after covering, curing the ionizing radiation-curable resin composition located between the transparent substrate film and the mold to produce a cured product of the ionizing radiation-curable resin composition;

09804081 071701
T0220 T8040860